

AMENDMENTS TO THE CLAIMS

This listing of claims will replace all prior versions, and listings, of claims in the application:

1. (Previously Presented) A thermoplastic resin composition which comprises (A) 1 to 50 parts by weight of a polytrimethylene terephthalate, ~~and (B) 99 to 50 parts by weight of a polycarbonate, wherein a crystallization enthalpy  $\Delta H_{cc}$  of component (A), which is obtained when the thermoplastic resin composition is heated from 0°C at 20°C/min, is 0 to 15 J/g, the crystallization enthalpy  $\Delta H_{cc}$  being calculated according to the following formula (I):~~

~~Crystallization peak area  $\Delta H$  measured using a DSC (J/g) / the content of component (A) based on the total amount of the thermoplastic resin composition (wt%)  $\times 100 = \Delta H_{cc}$  (J/g) (I)~~

and 0.1 to 10 parts by weight of a polyalkylene terephthalate resin (C) based on 100 parts by weight of the component (B), said polyalkylene terephthalate resin excluding polytrimethylene terephthalate, and

wherein components (A) and (C) have a crystallization enthalpy  $\Delta H_{cc}$ , which is obtained when the thermoplastic resin composition is heated from 0°C at 20°C/min, of 0 to 15 J/g, the crystallization enthalpy  $\Delta H_{cc}$  determined according to formula (II):

Crystallization peak area  $\Delta H$  measured using a DSC (J/g) / (Sum of the content of component (A) (wt%) and the content of component (C) (wt%) based on the total amount of the thermoplastic resin composition)  $\times 100 = \Delta H_{cc}$  (J/g) (II).

2. (Original) The thermoplastic resin composition according to claim 1, wherein a crystallization temperature  $T_c$  of the thermoplastic resin composition, which is obtained when the thermoplastic resin composition in a molten state at 270°C is cooled at -20°C/min, is 145°C or more.

3. (Original) The thermoplastic resin composition according to claim 1, wherein a crystallization temperature  $T_c$  of the thermoplastic resin composition, which is obtained when the thermoplastic resin composition in a molten state at 270°C is cooled at -20°C/min, is 175°C or more.

4. (Canceled)

5. (Previously Presented) The thermoplastic resin composition according to claim 1, wherein the thermoplastic resin composition is produced by melt-kneading 2 to 99 parts by weight of a resin composition (D), which comprises 50 to 99 parts by weight of component (A) and 50 to 1 parts by weight of component (B), and 98 to 1 parts by weight of component (B), provided that component (D) + component (B) = 100 parts by weight.

6. (Canceled)

7. (Currently Amended) The thermoplastic resin composition according to claim ~~6~~ 1, wherein component (C) is a polyethylene terephthalate resin and/or a polybutylene terephthalate resin.

8. (Previously Presented) A resin molded article which is produced by molding the thermoplastic resin composition according to claim 1.

9-11. (Canceled)

12. (Previously Presented) A method for producing the thermoplastic resin composition according to claim 1, wherein said method comprises melt-kneading 2 to 99 parts by weight of a resin composition (D), which comprises 50 to 99 parts by weight of component (A) and 50 to 1 parts by weight of component (B), and 98 to 1 parts by weight of component (B), provided that component (D) + component (B) = 100 parts by weight.

13. (Previously Presented) A method for molding the resin molded article according to claim 8, wherein said method comprises dry blending 2 to 99 parts by weight of a resin composition (D), which comprises 50 to 99 parts by weight of component (A) and 50 to 1 parts by weight of component (B), and 98 to 1 parts by weight of component (B), provided that component (D) + component (B) = 100 parts by weight), and subsequently molding and shaping the dry-blended product.

14. (Currently Amended) A resin molded article which is produced by molding the thermoplastic resin composition according to claim 6 1.

15. (Previously Presented) The resin molded article according to claim 14, wherein a crystallization enthalpy  $\Delta H_{cc}$  of components (A) and (C), which is obtained when the resin molded article is heated from 0°C at 20°C/min, is 0 to 15 J/g, the crystallization enthalpy  $\Delta H_{cc}$  being calculated according to the following formula (IV):

Crystallization peak area  $\Delta H$  measured using a DSC (J/g) / (Sum of the content of component (A) (wt%) and the content of component (C) (wt%) based on the total amount of the resin molded article)  $\times 100 = \Delta H_{cc}$  (J/g) (IV).

16. (Previously Presented) The resin molded article according to claim 14, wherein a crystallization temperature  $T_c$  of the resin molded article, which is obtained when resin molded article in a molten state at  $270^{\circ}\text{C}$  is cooled at  $-20^{\circ}\text{C}/\text{min}$ , is  $145^{\circ}\text{C}$  or more.

17. (Previously Presented) The resin molded article according to claim 14, wherein a crystallization temperature  $T_c$  of the resin molded article, which is obtained when the resin molded article in a molten state at  $270^{\circ}\text{C}$  is cooled at  $-20^{\circ}\text{C}/\text{min}$ , is  $175^{\circ}\text{C}$  or more.